

QUALITY ALLOYS
FOR
CORE SECTOR



VeeKay Smelters Pvt. Ltd

PRODUCT RANGE

Low Carbon Ferro Chrome

GRADE	Cr %	C %	Si %	P %	S %
008 FeCr 55		0.05 - 0.10			
03 FeCr 55	55 - 60	0.10 - 0.50			
08 FeCr 55		0.50 - 0.80	1.5max	0.05max	0.05max
008 FeCr 64		0.05 - 0.10			
03 FeCr 64	60 - 67	0.10 - 0.80			
08 FeCr 64		0.50 - 0.80			

Chrome Metal (AT)

GRADE	Cr %	C %	Si %	P %	S %
Cr97C06	98.6 min	0.06max	0.5max	0.05max	0.05max

Low Carbon Ferro Manganese

GRADE	Mn %	C %	Si %	P %	S %
2 Fe Mn 80	78 - 82	1.0 - 3.0			
2 Fe Mn 76	74 - 78	1.0 - 3.0			
01 Fe Mn 83		0.10 max			
02 Fe Mn 83		0.20 max	1.5 max	0.35 max	0.05max
03 Fe Mn 83	80 - 85	0.30 max			
05 Fe Mn 83		0.50 max			
07 Fe Mn 83		0.07 max			

PRODUCT RANGE

Ferro Titanium

GRADE	Ti %	C %	Si %	P %	S %
FeTi38	35 - 40				
FeTi32	30 - 35	0.10 max	3.0max	0.10 max	0.06 max
FeTi28	25 - 30				

Ferro Molybdenum

GRADE	Mo %	C %	Si %	P %	S %
Fe Mo 57C50	55 - 60				
Fe Mo 63C50	60 - 65	0.5max	1.50 max	0.10 max	0.06 max
Fe Mo 67C50	65 - 70				
Fe Mo 63C10	60 - 65	0.1max	2.0 max	0.06 max	0.08 max
Fe Mo 67C10	65 - 70				

High Carbon Ferro Manganese

GRADE	Mn %	C %	Si %	P %	S %
Fe Mn 76	74 - 78				
Fe Mn 72	70 - 74	8.0 max	1.5 max	0.35 max	0.05 max
Fe Mn 68	65 - 70				

Silico Manganese

GRADE	Mn %	C %	Si %	P %	S %
Si18Mn68	65 - 70		16 -20		
Si16Mn63	60 - 65	2.0 max	14 - 17	0.30 max	0.03 max
Si19Mn63	60 - 65		16 - 20		



Contact :

VeeKay Smelters Pvt. Ltd

Plot No : 9, Survey No : 912,
IDA, APIIC Industrial Park, Phase III
Peddapuram - 533437, E.G.Dist.,
Andhra Pradesh, India

Ph: +91 884 2388664, Fax : +91 884 2388662

Email: mail@veekaysmelters.com

Visit Us : www.veekaysmelters.com